

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09D 151/00, 133/06		A1	(11) International Publication Number: WO 96/22339
			(43) International Publication Date: 25 July 1996 (25.07.96)
(21) International Application Number: PCT/EP96/00107		(81) Designated States: BR, CA, CN, KR, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 11 January 1996 (11.01.96)			
(30) Priority Data: 7/7692 20 January 1995 (20.01.95) JP		Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(71) Applicants (for all designated States except US): BASF LACKE + FARBEN AG [DE/DE]; Glasuritstrasse 1, D-48165 Münster (DE). NIPPON OIL & FATS CORPORATION [JP/JP]; 1-10-1, Yuradku-cho, Chiyoda-ku, Tokyo-to (JP).			
(72) Inventors; and			
(75) Inventors/Applicants (for US only): MATSUKURA, Yoshiaki [JP/JP]; 1113 Shimokurata-chyou, Totsuka-ku, Tokohama-City, Kanagawa-ken (JP). TANIGUCHI, Hitoshi [JP/JP]; 430-34 Totsuka-ku, Yokohama-City, Kanagawa-ken (JP). SAKAI, Atsuhiko [JP/JP]; 1-12-12, Higashi-Kashiwagaya, Ebina-shi, Kanagawa (JP). KAWAMURA, Yoshiaki [JP/JP]; 2-26-6-208, Kajiwara, Kamakura-shi, Kanagawa-ken (JP).			
(74) Agent: MÜNCH, Volker; BASF Lacke + Farben AG, Patente/Lizenzen/Dokumentation, Postfach 6123, D-48136 Münster (DE).			

(54) Title: **WATER-BASED PAINT COMPOSITION**

(57) Abstract

To obtain water-based paint compositions with which there is broad scope for design of the base resin, and which can be made low-solvent, and which are also easy to apply and have outstanding storage stability, and can also form paint film of outstanding water-resistance, durability and smoothness. Water-based paint composition which contains a water-dispersible acrylic graft copolymer (A) of acid value 10-30 mg and hydroxyl value 50-150, which is a graft copolymer in which an acrylic copolymer of acid value 35-120 mg KOH/g and hydroxyl value 50-150 mg KOH/g, and an acrylic copolymer of acid value ≤ 15 and hydroxyl value 50-150 are graft polymerized via chemical bonds, and internally non-crosslinked acrylic fine particles (B) of acid value 15-200 and hydroxyl value 15-200 which are a copolymer made by emulsion polymerizing α,β -ethylenic unsaturated monomer, with the proportions of the total resin solids in the paint being accounted for by each being 10-90 wt.% for component (A) and 10-90 wt.% for component (B).

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

Water-based paint composition

5

The present invention relates to a water-based paint composition which contains a water-dispersible acrylic graft copolymer and internally non-crosslinked acrylic fine particles, and especially to a water-based
10 paint composition suited to metallic paint for automobiles.

As the problem of pollution of the global environment has deepened in recent years, international
15 regulations regarding the discharge of organic solvents have become more and more stringent. Against this background water-based paint using water as a medium has stepped into the spotlight. In this context, the development of water-based metallic undercoats for
20 industrial painting and especially automobile painting has been regarded as advantageous, not only because it has the effect of decreasing the use of organic solvents but also from the point of view of finished appearance and cost-performance, and to date various
25 water-based undercoats have been developed.

When one looks at the history of the art of making water-based undercoats, the trend has been to adopt water-dispersible resins as base resins. This is
30 because water-based paints in the form of an aqueous dispersion have the advantage of giving the water-based undercoat the rheological properties it requires.

Water-based paints in the form of aqueous dispersions are characterized in that the basic resin
35 is present in the water as particles. These can be classified broadly into direct emulsions or indirect emulsions according to the method for preparing the basic emulsion. In the direct emulsion method particles are formed directly in water by emulsion polymerization
40 or suspension polymerization; in the indirect emulsion method the base resin is first prepared in a solvent

phase and then transferred to an aqueous phase.

Of these the direct emulsion method is very much more efficacious in eliminating solvents from water-based paint since no organic solvent is needed at the preparation stage, and the preparation of the base resin is also easy. However, because of the limitations imposed by preparing the base resin in water, it has the problems that the suitability of the starting materials employed for polymerization has a considerable effect, and scope for resin design is narrowed.

On the other hand, with the indirect emulsion method there is a large degree of freedom as to the starting materials which can be employed and wide scope for resin design, but on the other hand there are problems in that it is difficult to remove the organic solvent employed when preparing the base resin, and this hinders the production of low-solvent water-based undercoats.

In this connection, water-based paints using polymer fine particles obtained by emulsion polymerization are recorded in EP00387 A1 and EP0401565 A1.

However, although such water-based paints do not give rise to painting faults such as sagging or bittiness, etc., since the particles confer pseudoplastic or thixotropic properties, there is the problem that the viscosity of the paint is prone to rise after application to the object to be painted and rheological properties become inadequate, and consequently smoothness is inferior. They also have the problem that dispersibility of pigments is inferior and it is difficult to obtain paint films with an outstanding gloss. Moreover, because the emulsifier is present in the aqueous dispersion after obtaining the resin by emulsion polymerization, inferior water-resistance is a problem.

In Japanese Examined Patent H5-30867 a water-based paint composition is recorded which contains water-insoluble vinyl resin fine particles of mean
5 particle size 0.3-6 μm obtained by polymerizing at least one type of water-soluble resin selected from polyester resins, alkyd resins, vinyl resins, vinyl-modified polyester resins and vinyl-modified alkyd resins, with a polymerizable unsaturated monomer
10 in water by two-stage emulsion polymerization in the presence of a seeded emulsion.

However, this water-based paint composition has the problem that because it is formed by dispersing a water-insoluble resin storage stability is inferior
15 because it is prone to flocculate.

The purpose of the present invention is to offer a water-based paint composition which combines the features both of aqueous dispersion type water-based
20 paints obtained by direct emulsification and of aqueous dispersion type water-based paints obtained by indirect emulsification: namely, enabling broad scope for design of the base resin and low-solvent use, not producing blistering, sagging or bittiness, etc., offering out-
25 standing ease of application and storage stability, and also enabling formation of paint films with outstanding water-resistance, durability and smoothness.

A 2nd purpose of the present invention is to offer a water-based paint composition suitable as a metallic
30 paint, which confers pseudoplastic and thixotropic properties even when a large quantity of pigment is dispersed therein, does not produce blistering, sagging or bittiness, etc., offers outstanding ease of application, and also enables the formation of paint
35 films with outstanding water-resistance, durability and smoothness, and has outstanding storage stability.

The present invention is the following water-based paint compositions.

- (1) A water-based paint composition characterized in that it contains a water-dispersable acrylic graft copolymer (A) which is a graft copolymer of an acrylic copolymer (a1) which is a copolymer of α,β -ethylenic unsaturated monomers including an α,β -ethylenic unsaturated carboxylic acid and has an acid value of 35-120 mg KOH/g and a hydroxyl value of 50-150 mg KOH/g, and an acrylic copolymer (a2) which is a copolymer of α,β -ethylenic unsaturated monomers and has an acid value of ≤ 15 mg KOH/g and a hydroxyl value of 50-150 mg KOH/g, grafted via chemical bonds, which has an acid value of 10-30 mg KOH/g and a hydroxyl value of 50-150 mg KOH/g, and internally non-crosslinked acrylic fine particles (B) which are of a copolymer made by emulsion polymerization of α,β -ethylenic unsaturated monomers (b1) and have an acid value of 15-200 mg KOH/g and a hydroxyl value of 15-200 mg KOH/g, with the proportions within the total resin solids in the water-based paint composition which each accounts for being 10-90 wt% for the water-dispersible acrylic graft copolymer (A), and 10-90 wt% for the internally non-crosslinked acrylic fine particles (B).
- (2) A water-based paint composition recorded in (1) above, characterized in that it contains an amino resin (C) of a number-average molecular weight of ≤ 1000 , accounting for a proportion of 10-40 wt% of the total resin solids in the water-based paint composition.
- (3) A water-based paint composition recorded in (1) or (2) above, characterized in that it contains an organic thickener swelled by alkalis (D) at 0.1-5 wt% of the total resin solids in the water-based paint composition.
- (4) A water-based paint composition recorded in any of (1)-(3) above, characterized in that the glass transition temperature of the acrylic copolymer (a1) is -20 to $+50^{\circ}\text{C}$ and its number average molecular weight is 4500-9000, the glass transition temperature of the

water-dispersible acrylic graft copolymer (A) is -20 to +50°C and its number average molecular weight is 10,000 to 100,000, and that the mean particle size of the internally non-crosslinked acrylic fine particles (B) in an aqueous medium is 20-150 nm.

In the present invention the expressions "(meth)-acrylic acid" and "(meth)acrylate" indicate "acrylic acid and/or methacrylic acid" and "acrylate and/or methacrylate".

The acrylic graft copolymer (A) used in the present invention is a graft copolymer in which the main chain is a hydrophilic acrylic copolymer (a1), which is hydrated and becomes a stabilizing layer when dispersed in an aqueous medium, and a hydrophobic acrylic acid copolymer (a2), which becomes a dispersion layer on dispersion, is grafted to this as side chains via chemical bonds.

The acid value of this acrylic graft copolymer (A) is 10-30 mg KOH/g, and preferably 15-30 mg KOH/g, and its hydroxyl value is 50-150 mg KOH/g, and preferably 50-120 mg KOH/g. It is also desirable that the glass transition temperature is -20 to +50°C, and preferably -10 to +30°C, and that the number average molecular weight is 10,000-100,000, and preferably 10,000-50,000.

The acrylic copolymer (a1) which constitutes the main chain of the acrylic graft copolymer (A) is a copolymer of α,β -ethylenic unsaturated monomers including an α,β -ethylenic unsaturated carboxylic acid, and has an acid value of 35-120 mg KOH/g, and preferably 60-110 mg KOH/g, and a hydroxyl value of 50-150 mg KOH/g, and preferably 60-150 mg KOH/g. It is also desirable that the acrylic copolymer (a1) has a glass transition temperature of -20 to +50°C, and preferably -20 to +30°C, and a number average molecular weight of 4500-9000, and preferably 4800-7000.

The acrylic copolymer (a2) which constitutes the side chains of the acrylic graft copolymer (A) is also a copolymer of α,β -ethylenic unsaturated monomers, and has an acid value of ≤ 15 mg KOH/g, and preferably ≤ 10 mg KOH/g, and a hydroxyl value of 50-150 mg KOH/g, and preferably 50-120 mg KOH/g.

The acrylic graft copolymer (A) employed in the present invention has a structure in which an acrylic copolymer (a1) and an acrylic copolymer (a2) as described above are graft copolymerized via chemical bonds such as ester linkages, ether linkages or urethane linkages, etc.

The acrylic graft copolymer (A) employed in the present invention is employed as the base resin which becomes the film-forming constituent; any polymer which has the aforementioned constitution and property values can be employed, with no specific restriction as to the method for making it. For example, an acrylic graft copolymer (A-1) in which an acrylic copolymer (a2-1) from a monomer combination (mm-1) including an α,β -unsaturated monomer containing a glycidyl group (m-3) and an α,β -unsaturated monomer containing a hydroxyl group (m-4) is graft polymerized to an acrylic copolymer (a1-1) from an α,β -ethylenic unsaturated monomer containing a hydroxyl group (m-1) and an α,β -ethylenic unsaturated monomer containing a carboxyl group (m-2), or an acrylic graft copolymer (A-2) in which an acrylic copolymer (a2-2) from a monomer combination (mm-2) including copolymerizable unsaturated monomers (m-6) is graft polymerized to an acrylic copolymer (a1-2) containing unsaturated bonds, obtained by reacting the acrylic copolymer (a1-1) above with an α,β -ethylenic unsaturated monomer (m-5) containing a functional group which can react with carboxyl groups and/or hydroxyl groups, can be employed as the acrylic graft copolymer (A).

Water-dispersible acrylic graft copolymers (A-1) which can be employed as a preferred Component (A) will first be explained. In acrylic graft copolymers of (A-1), an α,β -ethylenic unsaturated monomer (m-1) containing a hydroxyl group and an α,β -ethylenic unsaturated monomer (m-2) containing a carboxyl group are essential components of the hydrophilic acrylic copolymer (a1) which becomes the stabilizing layer; and the acrylic graft copolymer (a1-1) can be made from these α,β -ethylenic unsaturated monomers and any other optionally used copolymerizable unsaturated monomer(s) (m-7) by a known solution polymerization method in the presence of a suitable polymerization initiator.

Examples of α,β -ethylenic unsaturated monomers (m-1) containing a hydroxyl group include hydroxyalkyl esters of (meth)acrylic acid, such as 2-hydroxyethyl (meth)acrylate, 2-hydroxypropyl (meth)acrylate and 3-hydroxypropyl (meth)acrylate, etc., polyether polyols such as polyethylene glycol and polypropylene glycol, etc., monoethers of α,β -unsaturated monomers containing a hydroxyl group such as 2-hydroxyethyl (meth)acrylate, etc., and lactone-modified α,β -ethylenic unsaturated monomers such as addition compounds of hydroxyalkyl esters of (meth)acrylic acid with 1-10 mols of a lactone such as ϵ -caprolactone or γ -caprolactone, etc. These can be employed singly or in combinations of 2 or more.

Examples of α,β -ethylenic unsaturated monomers (m-2) containing a carboxyl group include acrylic acid, methacrylic acid, crotonic acid, itaconic acid and maleic acid, etc. These can be employed singly or in combinations of 2 or more.

Other optionally used copolymerizable unsaturated monomers (m-7) include: esters, for example C_{1-18} alkyl esters of (meth)acrylic acid, such as methyl (meth)acrylate, ethyl (meth)acrylate, propyl (meth)acrylate,

isopropyl (meth)acrylate, butyl (meth)acrylate, hexyl (meth)acrylate, octyl (meth)acrylate and lauryl (meth)acrylate, etc.; alkoxyalkyl esters of (meth)acrylic acid, such as methoxybutyl acrylate, methoxyethyl (meth)acrylate and ethoxybutyl (meth)acrylate, etc.; amides of acrylic acid and methacrylic acid; (meth)acrylic acid amides such as N-methylol(meth)acrylamide and N-isobutoxymethylol(meth)acrylamide, etc.; and aromatic vinyl compounds such as styrene, α -methylstyrene and vinyltoluene, etc.

The acrylic copolymers (a1-1) can be obtained by solution polymerization according to an ordinary method using these monomers, in the presence of a known polymerization initiator, such as azobisisobutyronitrile, benzoyl peroxide, t-butyl peroxybenzoate, t-butyl peroxide or t-butylperoxy-2-ethylhexanoate, etc. This reaction is performed such that the acrylic copolymer (a1-1) produced has an acid value of 35-120 mg KOH/g, and preferably 50-110 mg KOH/g and a hydroxyl value of 50-150 mg KOH/g, and preferably 60-150 mg KOH/g. It is also desirable that the reaction is performed to give a glass transition temperature of -20 to +50°C, and preferably -20 to +30°C, and a number average molecular weight of 4500-9000, and preferably 4800-7000. As the reaction medium, toluene, methyl isopropyl ketone, ethylene glycol monoethyl ether, ethylene glycol monobutyl ether, propylene glycol monopropyl ether or propylene glycol monoethyl ether, etc., or a mixture of these, etc., can be employed.

When the acid value of the acrylic copolymer (a1-1) is less than 35 mg KOH/g its action as a stabilizing layer is inadequate and the resulting acrylic graft copolymers (A-1) become prone to flocculate in an aqueous medium so that storage stability is inferior; and when it exceeds 120 mg KOH/g

it becomes too hydrophilic and paint films formed from water-based paint compositions prepared from the resulting acrylic graft copolymers (A-1) are inferior in water-resistance.

5 When the hydroxyl value of the acrylic copolymer (a1-1) is less than 50 mg KOH/g there are insufficient points for crosslinking between the resulting acrylic graft copolymers (A-1) and the amino resin (C) used as a curing agent, and consequently paint films obtained
10 are inferior in resistance to chemicals; and when it exceeds 150 mg KOH/g the resulting acrylic graft copolymers (A-1) become excessively hydrophilic, and paint films formed from water-based paint compositions containing them are inferior in water-resistance.

15 Similarly, when the glass transition temperature of the acrylic copolymer (a1-1) is less than -20°C the resulting acrylic graft copolymers (A-1) are prone to
20 conglutinate in aqueous media, so that the storage stability of aqueous dispersions is inferior; and when the glass transition temperature exceeds +50°C the resulting acrylic graft copolymers (A-1) have a high softening point, and the smoothness of paint films from water-based paint compositions prepared from these is
25 inferior.

 When the number average molecular weight of the acrylic copolymer (a1-1) is less than 4500 it cannot form an adequate stabilizing layer and the storage stability of aqueous dispersions of resulting acrylic
30 graft copolymers (A-1) is inferior; and when it exceeds 9000 aqueous dispersions of the resulting graft copolymers (A-1) become highly viscous, the proportion of painted solids of water-based paint compositions prepared from these is lowered and they are inferior as
35 regards sagging.

 The acrylic graft copolymer (A-1) is obtained by reacting a monomer combination (mm-1) with the acrylic copolymer (a1-1) above. As the monomer combination

(mm-1) a monomer combination is employed in which the essential components are an α,β -ethylenic unsaturated monomer (m-3) containing a glycidyl group and an α,β -ethylenic unsaturated monomer (m-4) containing a hydroxyl group, combined if necessary with (an) other copolymerizable unsaturated monomer(s) (m-7), to give an acid value of ≤ 15 mg KOH/g, and preferably ≤ 10 mg KOH/g, and a hydroxyl value of 50-150 mg KOH/g and preferably 50-120 mg KOH/g.

10

Examples of α,β -ethylenic unsaturated monomers (m-3) containing a glycidyl group include glycidyl (meth)acrylate and allyl glycidyl ether, etc. Examples of α,β -ethylenic unsaturated monomers containing a hydroxyl group (m-4) and of other copolymerizable unsaturated monomers (m-7) have been cited in connection with the aforementioned acrylic copolymer (a1-1).

When the acid value of the monomer combination (mm-1) above exceeds 15 mg KOH/g the resulting acrylic graft copolymers (A-1) become highly viscous, the proportion of painted solids of water-based paint compositions prepared from these is lowered and they are inferior as regards sagging.

When the hydroxyl value of the monomer combination (mm-1) is less than 50 mg KOH/g there are insufficient points for crosslinking between the resulting acrylic graft copolymers (A-1) and the amino resin (C) used as a curing agent, and consequently paint films obtained are inferior in resistance to chemicals; and when it exceeds 150 mg KOH/g the resulting acrylic graft copolymers (A-1) become excessively hydrophilic, and the resulting paint films are inferior in water-resistance.

35

The reaction between the aforementioned acrylic copolymer (a1-1) and monomer combination (mm-1) is performed with a ratio of acrylic copolymer (a1-1) and monomer combination (mm-1), (a1-1)/(mm-1) (w/w) of

10/90 to 60/40, and preferably 20/80 to 40/60, and (m-3)/(a1-1) (mol/mol) 0.4-1.5, and preferably 0.8-1.2.

The number of mols of acrylic copolymer (a1-1) can be decided by calculation from the number average molecular weight (polystyrene basis) determined in the ordinary way by gel permeation chromatography.

When (a1-1)/(mm-1) (w/w) is less than 10/90 an adequate stabilizing layer is not formed, and aqueous dispersions of the resulting acrylic graft copolymers (A-1) have inferior storage stability; and when it exceeds 60/40 aqueous dispersions of the resulting acrylic graft copolymers (A-1) become very highly viscous, the proportion of painted solids of water-based paint compositions prepared from these acrylic graft copolymers (A-1) is lowered and they are inferior as regards sagging.

Similarly, when the molar ratio of the quantity of α,β -ethylenic unsaturated monomer (m-3) containing a glycidyl group in the combination relative to the acrylic copolymer (a1-1) is less than 0.4, the grafting reaction with the monomer combination (mm-1) becomes inadequate, and either dispersion of the resulting acrylic graft copolymer (A-1) in an aqueous medium becomes difficult, or the storage stability of the resulting water-based paint composition is inferior; and when it exceeds 1.5 gelling occurs and it is impossible to make an acrylic graft copolymer (A-1).

30

The reaction between the acrylic copolymer (a1-1) and the monomer combination (mm-1) can be performed by [graft copolymerizing] the acrylic graft copolymer (a1-1) and the monomer combination (mm-1) by a known solution polymerization method in an organic solvent. Thus, it can be performed by a known solution polymerization method in an organic solvent as a continuation of the preparation of the acrylic copolymer (a1-1) by adding the monomer combination to

35

the reaction liquor after making the acrylic copolymer (a1-1).

As the organic solvent, toluene, methyl isopropyl ketone, ethylene glycol monoethyl ether, ethylene glycol monobutyl ether, propylene glycol monopropyl ether or propylene glycol monoethyl ether, etc., or a mixture of these, etc., can be employed.

As the polymerization initiator for copolymerizing the monomer combination (mm-1) the same polymerization initiators given as examples in the making of the acrylic copolymer (a1-1) can be employed.

It is desirable that the combined concentration of acrylic copolymer (a1-1) and monomer combination (mm-1) in the reaction solution is 30-90 wt%, and preferably 50-80 wt%, and that the concentration of the polymerization initiator is 0.1-10 wt%, and preferably 0.5-5 wt%. It is also desirable that the reaction temperature is 20-180°C, and preferably 40-160°C, and that the reaction time is 1-10 hours.

The acid value, hydroxyl value, glass transition temperature and number average molecular weight of the resulting acrylic graft copolymer (A-1) can be adjusted by selecting the reaction conditions such as the types of acrylic copolymer (a1-1) and monomer combination (mm-1) employed and the quantities employed, the reaction temperature, the reaction time and the type and quantity of polymerization initiator employed.

In the reaction above graft polymerization is performed by ring opening addition which proceeds between the carboxyl groups of the acrylic copolymer (a1-1) and the glycidyl groups of the component (m-3) which contains a glycidyl group, and accompanying free radical polymerization of the different monomers (m-3), (m-4) and (m-7), to make an acrylic graft copolymer (A-1) in a single-stage reaction.

The acrylic graft copolymer (A-1) is a graft copolymer which can be made as described above, and is a water-dispersible acrylic graft copolymer which has
5 an acid value of 10-30 mg KOH/g, and preferably 15-30 mg KOH/g, and a hydroxyl value of 50-150 mg KOH/g, and preferably 50-120 mg KOH/g. It is also desirable that this acrylic graft copolymer (A-1) has a glass transition temperature of -20 to +50°C, and preferably
10 -10 to +30°C, and a number average molecular weight of 10,000-100,000 and preferably 10,000-50,000.

When the acid value of the acrylic graft copolymer (A-1) is less than 10 mg KOH/g it becomes difficult to
15 disperse in an aqueous medium, or storage stability is inferior; and when it exceeds 30 mg KOH/g the resulting aqueous dispersions become very highly viscous, the proportion of painted solids of water-based paint compositions prepared from these is lowered and they
20 are inferior as regards sagging.

When the hydroxyl value of the acrylic graft copolymer (A-1) is less than 50 mg KOH/g there are insufficient points for crosslinking between the resulting acrylic graft copolymers (A-1) and the amino
25 resin (C) used as a curing agent, and consequently paint films obtained are inferior in resistance to chemicals; and when it exceeds 150 mg KOH/g it becomes excessively hydrophilic and the paint films obtained are inferior in water-resistance.

30 Similarly, when the glass transition temperature of the acrylic graft copolymer (A-1) is less than -20°C the graft copolymer (A-1) is prone to conglutinate in aqueous media, so that the storage stability of aqueous
35 dispersions is inferior; and when the glass transition temperature exceeds +50°C the smoothness of paint films from water-based paint compositions containing this acrylic graft copolymer (A-1) is inferior.

When the number average molecular weight of the

acrylic graft copolymer (A-1) is less than 10,000 paint films formed from water-based paint compositions prepared from this acrylic graft copolymer (A-1) are inferior in resistance to chemicals; and when it
5 exceeds 100,000 there is a risk that gelling will occur when making the acrylic graft copolymer.

Aforementioned acrylic graft copolymers (A-2) which can be employed as preferred components (A) will
10 next be explained. Acrylic graft copolymers (A-2) are graft copolymers in which an acrylic copolymer (a1-2) containing unsaturated bonds, obtained by reacting an
aforementioned acrylic copolymer (a1-1) with an α,β -ethylenic unsaturated monomer (m-5) having a
15 functional group which can react with carboxyl groups and/or hydroxyl groups, and a monomer combination (mm-2) comprising copolymerizable unsaturated monomers (m-6), are graft polymerized.

20 As regards the α,β -ethylenic unsaturated monomers (m-5) above, concrete examples of α,β -ethylenic unsaturated monomers (m-5-1) which have a functional group which can react with hydroxyl groups include
 α,α -dimethylisopropenylbenzyl isocyanate and
25 methacryloyl isocyanate, etc. Concrete examples of α,β -ethylenic unsaturated monomers (m-5-2) which have a functional group which can react with carboxyl groups include glycidyl (meth)acrylate and allyl glycidyl ether, etc.

30

The reaction between the acrylic copolymer (a1-1) and a monomer (m-5) above is performed with a molar ratio (m-5)/(a1-1) of 0.4-1.5, and preferably 0.8-1.2, such that the acrylic copolymer (a1-2) containing
35 unsaturated bonds that is obtained has an acid value of 35-120 mg KOH/g, and preferably 50-150 mg KOH/g [sic], and a hydroxyl value of 50-150 mg KOH/g, and preferably 60-150 mg KOH/g. It is also desirable that the reaction is performed to give a glass transition temperature of

-20 to +50°C, and preferably -20 to +30°C, and a number average molecular weight of 4500-9000, and preferably 4800-7000. The number of mols of acrylic copolymer (a1-1) can be decided by calculation from the number
5 average molecular weight (polystyrene basis) determined in the ordinary way by gel permeation chromatography.

When the mol ratio above is less than 0.4 the grafting reaction with the monomer combination (mm-2)
10 becomes inadequate, and either dispersion of the resulting acrylic graft copolymer (A-2) in an aqueous medium becomes difficult, or the storage stability of the resulting water-based paint composition is inferior; and when it exceeds 1.5 gelling occurs and it
15 is impossible to make an acrylic graft copolymer (A-2).

When the acid value of the acrylic copolymer (a1-2) is less than 35 mg KOH/g its action as a stabilizing layer is inadequate and the resulting
20 acrylic graft copolymers (A-2) become prone to flocculate in an aqueous medium so that storage stability is inferior; and when it exceeds 120 mg KOH/g it becomes too hydrophilic and paint films formed from water-based paint compositions prepared from the
25 resulting acrylic graft copolymers (A-2) are inferior in water-resistance.

When the hydroxyl value of the acrylic copolymer (a1-2) is less than 50 mg KOH/g there are insufficient points for crosslinking between the resulting acrylic
30 graft copolymers (A-2) and the amino resin (C) used as a curing agent, and consequently paint films obtained are inferior in resistance to chemicals; and when it exceeds 150 mg KOH/g the resulting acrylic graft copolymers (A-2) become excessively hydrophilic and
35 paint films formed from water-based paint compositions containing them are inferior in water-resistance.

Similarly, when the glass transition temperature of the acrylic copolymer (a1-2) is less than -20°C the

acrylic graft copolymers (A-2) obtained are prone to
conglutinate in aqueous media, so that the storage
stability of aqueous dispersions is inferior; and when
the glass transition temperature exceeds +50°C the
5 resulting acrylic graft copolymers (A-2) have a high
softening point, and the smoothness of paint films from
water-based paint compositions prepared from these is
inferior.

When the number average molecular weight of the
10 acrylic copolymer (a1-2) is less than 4500 it cannot
form an adequate stabilizing layer and the storage
stability of aqueous dispersions of resulting acrylic
graft copolymers (A-2) is inferior; and when it exceeds
9000 aqueous dispersions of the resulting graft
15 copolymers (A-2) become highly viscous, the proportion
of painted solids of water-based paint compositions
prepared from these is lowered and they are inferior as
regards sagging.

20 The reaction of the acrylic copolymer (a1-1) and
the monomer (m-5) is preferably performed in the
presence of a catalyst such as dibutyltin diacetate,
dibutyltin dilaurate or dibutyltin diacetate, etc.

It is desirable that the combined concentration of
25 component (a1-1) and component (m-5) in the reaction
solution is 30-90 wt%, and preferably 50-80 wt%, and
that the concentration of catalyst in the reaction
liquid is 0.1-5 wt%, and preferably 0.1-2 wt%. It is
also desirable that the reaction temperature is
30 20-120°C, and preferably 40-140°C, and the reaction time
is 0.5-5 hours.

In the reaction above an acrylic copolymer (a1-2)
containing unsaturated bonds is made by reaction
35 between the hydroxyl groups of the acrylic copolymer
(a1-1) and the functional group of component (m-5)
which reacts with carboxyl groups or hydroxyl groups,
for example an isocyanate group or a glycidyl group, to
form chemical bonds by which component (m-5) is added

to the acrylic copolymer (a1-1).

The acrylic graft copolymer (A-2) is obtained by graft copolymerizing to an acrylic copolymer (a1-2) containing unsaturated bonds above a monomer combination (mm-2) combining copolymerizable unsaturated monomers (m-6) to give an acid value of ≤ 15 mg KOH/g, and preferably ≤ 10 mg KOH/g, and a hydroxyl value of 50-150 mg KOH/g, and preferably 60-120 mg KOH/g.

The copolymerizable unsaturated monomers (m-6) can be selected from the α, β -ethylenic unsaturated monomers (m-1) containing a hydroxyl group, α, β -ethylenic monomers (m-2) containing a carboxyl group and other copolymerizable unsaturated monomers (m-7) given as examples in connection with the aforementioned acrylic copolymer (a1-1).

When the acid value of the monomer combination (mm-2) above exceeds 15 mg KOH/g the resulting acrylic graft copolymers (A-2) become highly viscous, the proportion of painted solids of water-based paint compositions prepared from these is lowered and they are inferior as regards sagging.

When the hydroxyl value of the monomer combination (mm-2) is less than 50 mg KOH/g there are insufficient points for crosslinking between the resulting acrylic graft copolymers (A-2) and the amino resin (C) used as a curing agent, and consequently paint films obtained are inferior in resistance to chemicals; and when it exceeds 150 mg KOH/g it becomes excessively hydrophilic, and the resulting paint films are inferior in water-resistance.

The reaction between the aforementioned acrylic copolymer (a1-2) containing unsaturated bonds and monomer combination (mm-2) is performed with a ratio of acrylic copolymer (a1-2) containing unsaturated bonds and monomer combination (mm-2), (a1-2)/(mm-2) (w/w) of

10/90 to 60/40, and preferably 20/80 to 40/60, and
(m-3)/(a1-1) (mol/mol) 0.4-2.5, and preferably 0.8-2.2.
When this weight ratio is less than 10/90 an adequate
stabilizing layer is not formed, and aqueous
5 dispersions of the resulting acrylic graft copolymers
(A-2) have inferior storage stability; and when it
exceeds 60/40 aqueous dispersions of the resulting
acrylic graft copolymers (A-2) become very highly
viscous, the proportion of painted solids of
10 water-based paint compositions prepared from these
acrylic graft copolymers (A-2) is lowered and they are
inferior as regards sagging.

The reaction between the acrylic copolymer (a1-2)
15 and the monomer combination (mm-2) can make component
(a1-2) and the monomer combination (mm-2) by a known
solution polymerization method in a suitable reaction
medium [sic].

The graft polymerization reaction between
20 component (a1-2) and component (mm-2) can be performed
in the presence of a polymerization initiator by a
known method. As the polymerization initiator the same
polymerization initiators given as examples in the
making of the acrylic copolymer (a1-1) can be employed.

25 It is desirable that the combined concentration of
acrylic copolymer (a1-2) and monomer combination (mm-2)
in the reaction solution is 30-90 wt%, and preferably
50-80 wt%, and that the concentration of the
30 polymerization initiator is 0.1-10 wt%, and preferably
0.5-5 wt%, relative to the total weight. It is also
desirable that the reaction temperature is 20-180°C, and
preferably 40-160°C, and that the reaction time is 1-10
hours.

35 The acid value, hydroxyl value, glass transition
temperature and number average molecular weight of the
resulting acrylic graft copolymer (A-2) can be adjusted
by selecting the reaction conditions such as the types

of component (a1-2) and component (mm-2) employed and the quantities employed, the reaction temperature, the reaction time and the type and quantity of polymerization initiator employed.

5

In the reaction above graft polymerization is performed by copolymerization of the monomer combination (mm-2) with the unsaturated bonds in component (a1-2), to make the acrylic graft copolymer (A-2).

10

The acrylic graft copolymer (A-2) is a graft copolymer which can be made as described above, and is a water-dispersible acrylic graft copolymer which has an acid value of 10-30 mg KOH/g, and preferably 15-30 mg KOH/g, and a hydroxyl value of 50-150 mg KOH/g, and preferably 60-120 mg KOH/g. It is also desirable that this acrylic graft copolymer (A-2) has a glass transition temperature of -20 to +50°C, and preferably -10 to +30°C, and a number average molecular weight of 10,000-100,000 and preferably 10,000-50,000.

20

When the acid value of the acrylic graft copolymer (A-2) is less than 10 mg KOH/g it becomes difficult to disperse in an aqueous medium, or storage stability is inferior; and when it exceeds 30 mg KOH/g the resulting aqueous dispersions become very highly viscous, the proportion of painted solids of water-based paint compositions prepared from these is lowered and they are inferior as regards sagging.

30

When the hydroxyl value of the acrylic graft copolymer (A-2) is less than 50 mg KOH/g there are insufficient points for crosslinking between the resulting acrylic graft copolymers (A-2) and the amino resin (C) used as a curing agent, and consequently paint films obtained are inferior in resistance to chemicals; and when it exceeds 150 mg KOH/g it becomes excessively hydrophilic, and the paint films obtained are inferior in water-resistance.

35

Similarly, when the glass transition temperature of the acrylic graft copolymer (A-2) is less than -20°C the acrylic graft copolymer (A-2) is prone to
5 conglutinate in aqueous media, so that the storage stability of aqueous dispersions is inferior; and when the glass transition temperature exceeds $+50^{\circ}\text{C}$ the smoothness of paint films from water-based paint compositions containing this acrylic graft copolymer
10 (A-2) is inferior.

When the number average molecular weight of the acrylic graft copolymer (A-2) is less than 10,000 paint films formed from water-based paint compositions prepared from this acrylic graft copolymer (A-2) are
15 inferior in resistance to chemicals; and when it exceeds 100,000 there is a risk that gelling will occur when making the acrylic graft copolymer.

The acrylic graft copolymers (A) such as (A-1) and
20 (A-2) employed in the present invention can be made into aqueous dispersions by neutralizing with a basic substance and dispersion in an aqueous dispersion medium, after removing the solvent employed in making them if necessary. Dispersion in an aqueous dispersion
25 medium can be performed by an ordinary method: it can be performed for example by neutralizing at least 50% of the carboxyl groups present in the acrylic graft copolymer (A) by using monomethylamine, dimethylamine, trimethylamine, diethylenetriamine, diethanolamine,
30 dimethylethanolamine, piperazine, ammonia or sodium hydroxide, etc., for example as a basic substance. An aqueous dispersion medium in which water accounts for 40-80 wt% is preferred.

An aqueous dispersion thus obtained can be
35 combined as it stands, or after concentration or dilution or drying and resuspension, with internally non-crosslinked acrylic fine particles (B), an amino resin (C) and an alkali-swelling organic extender (D) described below, etc., to prepare a water-based paint

composition.

The internally non-crosslinked fine particles (B) employed in the present invention are internally
5 non-crosslinked fine particles made by performing free radical polymerization of α,β -ethylenic unsaturated monomers (b1) by a known emulsion polymerization method in an aqueous medium in the presence of a surfactant, and besides being employed as a basic resin which
10 becomes the film-forming component of the water-based paint composition, are a component which confers pseudoplastic or thixotropic properties on the water-based paint composition.

15 The copolymerization here can be performed with an α,β -ethylenic unsaturated monomer (b1-1) containing a carboxyl group and an α,β -ethylenic unsaturated monomer (b1-2) containing a hydroxyl group as essential components, and other copolymerizable monomers as
20 required. As these monomers the same monomers indicated in connection with the aforementioned acrylic copolymer (a1-1) can be employed.

There is no specific restriction as to the method for emulsion polymerization, examples of which include
25 seeded polymerization, 2-stage emulsion polymerization, 2-stage polymerization in the presence of a seeded emulsion, and the power feed method, etc.

The surfactant employed for emulsion
30 polymerization is preferably an anionic or non-ionic surfactant. Examples of such surfactants include sodium dodecylbenzenesulfonate, ammonium dodecylbenzenesulfonate, ammonium polyoxyethylene lauryl ether sulfate, sodium alkylphenylpolyoxyethylene
35 sulfate, ammonium alkylphenylpolyoxyethylene sulfate, polyoxyethylene oleyl ether and polyoxyethylene tridecyl ether, etc. The quantity of surfactant added will differ depending on the emulsifying capacity of the surfactant employed and the particle size of the

internally non-crosslinked acrylic fine particles (B) to be obtained as a result, but it is generally in the range 0.05-5 wt%, and preferably 0.1-4 wt% relative to the water.

5 There is no specific restriction as to the polymerization initiator employed for emulsion polymerization, and organic peroxides, inorganic peroxides, azo type polymerization initiators and redox type polymerization initiators can be employed:
10 examples include benzoyl peroxide, t-butyl peroxybenzoate, t-butyl peroxyoctanoate, ammonium persulfate, sodium persulfate, and the ferrous salt of hydrogen peroxide, etc.

15 The internally non-crosslinked acrylic fine particles employed are particles (B) having an acid value of 15-200 mg KOH/g, and preferably 20-100 mg KOH/g, and a hydroxyl value of 15-200 mg KOH/g, and preferably 20-100 mg KOH/g. It is also desirable that
20 particles with a glass transition temperature a -20 to +50°C, and preferably 0 to +30°C, and a mean particle size in an aqueous medium of 20-150 nm, and preferably 50-100 nm, are employed.

25 When the acid value is less than 15 mg KOH/g there is a proneness to flocculate, so that the storage stability of the water-based paint composition is inferior. The benefits in conferring pseudoplastic or thixotropic properties on the water-based paint
30 composition are also weakened, aluminum bittiness is prone to be produced and ease of application is inferior. On the other hand, when the acid value exceeds 200 mg KOH/g they become excessively hydrophilic and the water-resistance of the resulting
35 paint films is inferior.

When the hydroxyl value is less than 15 mg KOH/g there are insufficient points of crosslinking with the amino resin (C) and the resulting paint films are inferior in chemical resistance; and when the hydroxyl

value exceeds 200 mg KOH/g they become excessively hydrophilic and consequently the water-resistance of the resulting paint films is inferior.

5 Similarly, when the glass transition temperature is less than -20°C the acrylic fine particles (B) are prone to conglutinate in aqueous media, so that the storage stability of aqueous dispersions is inferior; and when the glass transition temperature exceeds 50°C
10 the smoothness of paint films is inferior.

 When the particle size of the acrylic fine particles (B) is less than 20 nm a large quantity of surfactant is necessary for making them and therefore the water-resistance of the resulting paint films is
15 inferior. On the other hand, when the particle size exceeds 150 nm the surface area effect of the acrylic fine particles (B) is considerably decreased, the benefits in conferring pseudoplastic or thixotropic properties on the water-based paint compositions are
20 weakened, aluminum bittiness is prone to be produced and ease of application is inferior.

 The amino resin (C) employed in the present invention is an amino resin of a number average
25 molecular weight of ≤ 1000 , and preferably 300-800, and is the crosslinking component (curing agent) of the water-based paint composition. Examples of such amino resins (C) include the commercial products Cymel 301, Cymel 303, Cymel 325 and Cymel 327 (trade names Mitsui
30 Scitec KK), Nikalac MW-30 and Nikalac MX43 (trade names Sanwa Chemical KK) and Yuban 120 (trade name Mitsui Toatsu Chemicals), etc. The number average molecular weight of the amino resin (C) is the number average molecular weight based on polystyrene, determined by
35 gel-permeation chromatograph according to the normal method. When the number average molecular weight (C) of the amino resin (C) exceeds 1000 it is difficult to disperse in aqueous media and the stability of the water-based paint composition is inferior.

The organic thickener swelled by alkalis (D) employed in the present invention is a component which confers further pseudoplastic or thixotropic properties on the water-based paint composition, and it is particularly efficacious when including a phosphorescent pigment in the water-based paint composition as in metallic paint compositions. Examples of organic thickeners swelled by alkalis (D) include ASE-60 (trade name Rohm and Haas) and Thickenol-150B (trade name Kyoei Chemical), etc.

Water-based paint compositions of the present invention comprise aqueous dispersions containing an aforementioned water-dispersible acrylic graft copolymer (A) and internally non-crosslinked acrylic fine particles (B) as essential components, and optionally also an amino resin (C) and/or a thickener swelled by alkalis (D).

When it does not contain component (C) the contents of component (A) and component (D) in the total resin solids of the water-based paint composition are 10-90 wt%, and preferably 40-80 wt%, for component (A) and 10-90 wt%, and preferably 20-60 wt% for component (B). When it contains (C) there is 20-80 wt%, and preferably 30-70 wt%, of component (A), 20-80 wt%, and preferably 30-70 wt%, of component (B), and 10-40 wt%, and preferably 20-40 wt%, of component (C).

The content of component (D) is 0.1-5 wt%, and preferably 0.5-4 wt%, of the total resin solids in the water-based paint composition.

With less than the lower limit of component (A) the primary resin in the water-based paint composition is inadequate and the basic performance of the resulting paint film is inferior. On the other hand, when it exceeds the upper limit above the action of component (B) is considerably damaged and ease of application of the water-based paint composition is

inferior.

With less than the lower limit of component (B) the benefits in terms of conferring pseudoplasticity or thixotropy on the water-based paint composition are weakened and ease of application is inferior. On the other hand, when it exceeds the upper limit above, the quantity of surfactant included in the water-based paint composition is increased and the water-resistance of the resulting paint film is inferior.

When component (C) is within the range above, the resulting paint film show even better resistance to chemicals and resilience than when component (C) is not included.

Component (D) is efficacious in the preparation of metallic paint compositions; when the content thereof is less than 0.1 wt% brittiness is produced, and when it exceeds 5 wt% the water-resistance of the paint film is inferior because of the high acid value of component (D).

Organic solvents can optionally be added to a water-based paint composition of the present invention. Examples of such organic solvents include ethylene glycol monoethyl ether, ethylene glycol monobutyl ether, diethylene glycol mono[no]butyl ether, ethylene glycol monohexyl ether, propylene glycol monomethyl ether, propylene glycol monoethyl ether and propylene glycol monobutyl ether, etc.

Metallic pigments, inorganic pigments and/or organic pigments, etc., can also optionally be added. There is no specific restriction as to the method of adding pigments, and this can be performed by a known method. Moreover, other known additives added to water-based paints, such as acid catalysts, surface regulators and/or blistering inhibitors, etc., can also optionally be included.

Water-based paint compositions of the present invention have extremely outstanding storage stability,

there are easy to apply because they have pseudoplastic and/or thixotropic properties, and paint films obtained from them have excellent paint film performance traits such as water-resistance, durability and smoothness, etc.

Water-based paint compositions of the present invention can primarily be employed as undercoats for automobiles, and in this case they can be handled in the same way as ordinary undercoats, and they can particularly suitably be employed in prior known 2-coats 1-bake painting systems in which the undercoat and the top coat are applied wet-on-wet and then the two are baked at the same time.

The benefits recorded in the present invention can be obtained when the various numerical ranges hitherto explained, for example the property values of the acrylic copolymers and monomer combinations, the proportions in which they are reacted, the property values of the acrylic graft copolymer (A), and the contents of components (A)-(D), etc., are in the ranges recorded; and particularly outstanding benefits can be obtained when the numerical ranges of the different values are the ranges defined as the preferred ranges.

By using as the base resin an acrylic graft copolymer (A) in which a component of high acid value and a component of low acid value are chemically linked, and further including internally non-crosslinked acrylic fine particles (B), water-based paint compositions of the present invention allow broad scope for base resin design and low solvent use, they do not produce blistering, sagging or bittiness, and they give paint films of outstanding water-resistance, durability and smoothness etc.

Including an amino resin (C) in a water-based paint composition of the present invention further improves the resilience of the paint film and its resistance to chemicals.

Including a thickener swelled by alkalis (D) in a water-based composition of the present invention confers further pseudoplasticity and thixotropy when phosphorescent pigments are included as in a metallic paint composition, and improves ease of application.

The present invention will next be explained in even more detail by means of practical embodiments; however, these embodiments do not imply any restrictions as to the scope of the present invention. In the examples "parts" indicates "parts by weight" except where specifically stated otherwise. The method of application and the methods for evaluating paint film appearance, paint film performance and storage stability are as follows.

The following were used as test sheets to be painted. Thus, sheet steel treated with zinc phosphate, electrocoated with a cathodic deposition paint (Aqua No. 4200; trade name Nippon Oil & Fats) to give a dry film thickness of 20 μm , baked at 175°C for 20 minutes, air sprayed with a middle coat paint (Haiepiko No. 100 CP Sealer; trade name Nippon Oil & Fats) to give a dry film thickness of 40 μm and baked at 140°C for 20 minutes was used.

These test sheets were painted with the water-based paint compositions prepared in the different examples by the known 2-coats 1-bake method. Thus, the water-based paint composition was spray-coated in a painting environment at a temperature of 25°C and a relative humidity of 75% to give a dry film thickness of approximately 15 μm , followed by drying by heating at a temperature of 80°C for 10 minutes, cooling to room temperature, and then spray coating with a commercial clear top coat (Belcoat No. 6000; trade name Nippon Oil & Fats) to give a dry film thickness of approximately 40 μm followed, after setting for 10 minutes, by baking at 140°C for 30 minutes. The object to be painted was held

perpendicular throughout the entire process.

1) 60° Gloss

JIS K5400 (1990) 7.6 mirror-surface gloss.

5 2) Smoothness

The paint film was observed visually and evaluated using the following criteria.

o : satisfactory

x : inferior

10 3) Aluminum bittiness

The paint film was observed visually and evaluated using the following criteria.

o : no bittiness

x : bittiness

15 4) Sagging

A hole 10 mm in diameter was opened in the object to be painted and the length of sagging under the hole after painting to give a dry film thickness of 20 μ m was assessed according to the following criteria.

20 o : less than 2 mm

x : ≥ 2 mm

1) Water-resistance

25 The state of the painted surface was observed visually after immersion for 4 hours in hot water at 90°C, and evaluated according to the following criteria.

o : no abnormality

x : blistering

2) Resistance to chemicals

30 The state of the painted surface was observed visually after immersion for 1 hour in regular petrol at 40°C, and evaluated according to the following criteria.

o : no abnormality

35 x : shrinkage

3) Resilience

Evaluated by JIS K5400 (1990) 8.3 Dupont impact resistance, assessed according to the following criteria after dropping the weight from a height of 20

cm.

- o : not able to be cracked or detached
x : cracking or detachment produced

5 Evaluated by the change (%) in viscosity of the water-based paint composition after storage at 40°C for 20 days compared with initial viscosity (ps/6 rpm (B type viscosimeter)), according to the following criteria.

- 10 o : less than $\pm 15\%$
 x : $\geq \pm 15\%$

Preparation example 1-1 [Making an acrylic graft copolymer (A-1)]

15 Methyl isopropyl ketone 56.4 parts was put into a reaction vessel equipped with a stirrer, a temperature regulator, a cooling tube and a dropping device, stirred as the temperature was raised, and refluxed. A mixture of 41.8 parts of 2-hydroxyethyl methacrylate,
20 11.6 parts of acrylic acid, 93.6 parts of n-butyl acrylate, 33.0 parts of 2-ethylhexyl methacrylate and 3.6 parts of azobisisobutyronitrile was then added dropwise over 2 hours. Stirring under reflux was continued for a further 2 hours to complete the
25 polymerization (this reaction process is termed "Process 1" hereafter).

 The resin obtained was an acrylic copolymer having an acid value of 50 mg KOH/g, a hydroxyl value of 100 mg KOH/g, a glass transition temperature of -20°C and a
30 number average molecular weight of 5000.

 A further 328.6 parts of methyl isobutyl ketone was then added to this resin solution, and it was stirred under reflux. A mixture of 5.1 parts of
35 glycidyl methacrylate, 97.5 parts of 2-hydroxyethyl methacrylate, 200.2 parts of methyl methacrylate, 122.3 parts of n-butyl acrylate and 6.3 parts of azobisisobutyronitrile was then added dropwise over 2 hours. After further stirring for 1 hour at a reaction

temperature of 120°C, the temperature was raised to 130°C and the addition and copolymerization reactions were completed by continuing stirring for a further 5 hours (this reaction process is termed "Process 2" hereafter).

The resin solution obtained was a resin solution which included an acrylic graft copolymer A-1-1 having an acid value of 12 mg KOH/g, a hydroxyl value of 100 mg KOH/g, a glass transition temperature of +13°C and a number average molecular weight of 42,000.

Preparation Examples 1-2 to 1-4 [Making an acrylic graft copolymer (A-1)]

Acrylic graft copolymers A-1-2 to A-1-4 were made by the same method as in Preparation Example 1-1, according to the formulations in Table 1 or Table 2.

Acrylic graft copolymer No.	A-1-1	A-1-2
<u>Process 1 (parts by weight)</u>		
<u>Solvent composition</u>		
Methyl isopropyl ketone	56.4	155.2
Toluene	-	-
<u>Monomer composition</u>		
2-Hydroxyethyl methacrylate	41.8	55.7
Acrylic acid	11.6	15.4
n-Butyl acrylate	93.6	124.9
2-Ethylhexyl methacrylate	33.0	44.0
Styrene	-	-
<u>Initiator</u>		
Azobisisobutyronitrile	3.6	4.8
t-BPOEH *1	-	-
t-butyl peroxybenzoate	-	-
Reaction temperature	reflux	reflux
<u>Process 2 (parts by weight)</u>		
<u>Solvent composition</u>		
Methyl isopropyl ketone	328.6	227.6
Toluene	-	-
Ethylene glycol monobutyl ether	-	-
<u>Monomer composition</u>		
2-Hydroxyethyl methacrylate	97.5	83.6
Acrylic acid	-	-
Methyl methacrylate	200.2	171.6
n-Butyl acrylate	122.3	104.8
Styrene	-	-
Glycidyl methacrylate	5.1	7.0
<u>Initiator</u>		
Azobisisobutyronitrile	6.3	5.4
t-BPOEH *1	-	-
t-butyl peroxybenzoate	-	-
Reaction temperature	reflux	reflux
<u>Properties of component (a1-1) obtained by Process 1</u>		
Acid value	(mg KOH/g) 50	50
Hydroxyl value	(mg KOH/g) 100	100
Glass transition temperature	(°C) -20	-20
Number average molecular weight	5000	4900
<u>Properties of monomer combination (a2-1) polymerized in Process 2</u>		
Acid value	(mg KOH/g) 0	0
Hydroxyl value	(mg KOH/g) 100	100
Glass transition temperature	(°C) +30	+30
<u>Properties of the acrylic graft copolymer</u>		
Acid value	(mg KOH/g) 12	15
Hydroxyl value	(mg KOH/g) 100	100
Glass transition temperature	(°C) +13	+8
Number average molecular weight	42000	32000
Component (a1-1)/component (m-1) (w/w)	30/70	40/60
Component (m-3)/component (a1-1) mol ratio	1.0	1.0

*1 t-BPOEH : t-Butylperoxy-2-ethylhexanoate

[Table 2]

Acrylic graft copolymer No.	A-1-3	A-1-4
<u>Process 1 (parts by weight)</u>		
<u>Solvent composition</u>		
Methyl isopropyl ketone	-	77.9
Toluene	77.0	-
<u>Monomer composition</u>		
2-Hydroxyethyl methacrylate	27.9	41.8
Acrylic acid	15.4	15.4
n-Butyl acrylate	28.7	3.2
2-Ethylhexyl methacrylate	48.0	47.6
Styrene	-	12.0
<u>Initiator</u>		
Azobisisobutyronitrile	-	-
t-BPOEH *1	3.0	-
t-butyl peroxybenzoate	-	3.6
Reaction temperature	reflux	reflux
<u>Process 2 (parts by weight)</u>		
<u>Solvent composition</u>		
Methyl isopropyl ketone	-	303.0
Toluene	156.9	-
Ethylene glycol monobutyl ether	150.0	-
<u>Monomer composition</u>		
2-Hydroxyethyl methacrylate	111.4	110.9
Acrylic acid	-	-
Methyl methacrylate	228.8	134.9
n-Butyl acrylate	139.8	138.2
Styrene	-	96.0
Glycidyl methacrylate	3.5	3.5
<u>Initiator</u>		
Azobisisobutyronitrile	-	-
t-BPOEH *1	9.6	-
t-butyl peroxybenzoate	-	12.0
Reaction temperature	120°C	reflux
<u>Properties of component (a1-1) obtained by Process 1</u>		
Acid value (mg KOH/g)	100	100
Hydroxyl value (mg KOH/g)	100	150
Glass transition temperature (°C)	0	+30
Number average molecular weight	4900	4800
<u>Properties of monomer combination (a2-1) polymerized in Process 2</u>		
Acid value (mg KOH/g)	0	0
Hydroxyl value (mg KOH/g)	100	100
Glass transition temperature (°C)	+30	+30
<u>Properties of the acrylic graft copolymer</u>		
Acid value (mg KOH/g)	18	20
Hydroxyl value (mg KOH/g)	100	107
Glass transition temperature (°C)	+23	+30
Number average molecular weight	34000	31000
Component (a1-1)/component (m-1) (w/w)	20/80	20/80
Component (m-3)/component (a1-1) mol ratio	1.0	1.0

*1 t-BPOEH : t-Butylperoxy-2-ethylhexanoate

Preparation Example 2-1 [Making an aqueous dispersion]

Ethylene glycol monobutyl ether 80 parts was added to 533 parts of acrylic graft copolymer A-1-1 obtained
5 in Preparation Example 1-1, and then 205 parts of methyl isopropyl ketone was distilled off under decreased pressure. Dimethylethanolamine 3.0 parts (equivalent to 50% of the carboxyl groups) was added to this polymer solution, and after stirring 588.9 parts
10 of deionized water was added and stirred to give an even dispersion and obtain a milky white low-viscosity aqueous dispersion A-1-1aq of the acrylic graft copolymer A-1-1 (see Table 7).

15 Preparation Example 2-1 to 2-4 [Making an aqueous dispersion]

Aqueous dispersions A-1-2aq to A-1-4aq of acrylic graft copolymers A-1-2 to A-1-4 were obtained by the same method as in Preparation Example 2-1 with the
20 combinations shown in Table 7.

Table 3

Aqueous dispersion No.	A-1-1aq		A-1-2aq		A-1-3aq		A-1-4aq	
	A-1-1		A-1-2		A-1-3		A-1-4	
Type of acrylic graft copolymer								
Graft copolymer included	533.0		533.0		533.0		533.0	
Ethylene glycol monobutyl ether	80.0		80.0		-		80.0	
Methyl isopropyl ketone distilled off under decreased pressure	205.0		204.0		-		205.0	
Toluene distilled off under decreased pressure	-		-		124.0		-	
Dimethylethanamine	3.0		3.8		4.6		5.1	
Deionized water	588.9		587.2		586.4		586.9	
Nature of the aqueous dispersion obtained	milky white low-viscosity liquid		milky white low-viscosity liquid		milky white low-viscosity liquid		milky white low-viscosity liquid	

Note 1 : Low-viscosity means ≤ 1 ps at 25°C

Note 2 : Units parts by weight

Preparation Example 5-1 [Making an acrylic graft copolymer (A-2)]

Toluene 116.4 parts was put into a reaction vessel equipped with a stirrer, a temperature regulator, a cooling tube and a dropping device, stirred as the temperature was raised, and refluxed. A mixture of 41.8 parts of 2-hydroxyethyl methacrylate, 18.5 parts of acrylic acid, 64.3 parts of n-butyl acrylate, 55.4 parts of n-butyl methacrylate and 3.6 parts of azobisisobutyronitrile was added dropwise over 2 hours. Then stirring was continued for a further 2 hours to complete the polymerization (this reaction process is termed "Process (1)" hereafter).

Next, 7.4 parts of α,α -dimethylisopropenylbenzyl isocyanate and 0.1 part of dibutyltin dilaurate were put into this resin solution, and stirring was continued for 1 hour at 80°C (this reaction process is termed "Process (2)" hereafter).

The resin obtained was an acrylic copolymer having an acid value of 80 mg KOH/g, a hydroxyl value of 100 mg KOH/g, a glass transition temperature of 0°C and a number average molecular weight of 4900.

Then 266.2 parts of toluene were put into this resin solution and it was stirred under reflux. Then a mixture of 97.4 parts of 2-hydroxyethyl methacrylate, 173.4 parts of n-butyl acrylate, 149.2 parts of methyl methacrylate and 6.3 parts of azobisisobutyronitrile was added dropwise to this resin solution over 2 hours. The reaction was completed by continuing stirring for a further 2 hours (this reaction process is termed "Process (3)" below).

The resin solution obtained was a resin solution containing an acrylic graft copolymer A-2-1 having an acid value of 24 mg KOH/g, a hydroxyl value of 96 mg KOH/g, a glass transition temperature of +7°C and a number average molecular weight of 32,000 (see Table 4 to Table 6).

Preparation Example 3-2 to 3-4 [Making an acrylic graft copolymer (A-2)]

5 Acrylic graft copolymers A-2-2 to A-2-4 were made by the same method as in Preparation Example 3-1, with the formulations in Table 4 to Table 6. Properties, etc., are shown in Table 4 to Table 6.

Table 4

Acrylic graft copolymer No.	(parts by weight)			
	A-2-1	A-2-2	A-2-3	A-2-4
Process 1				
<u>Solvent</u>				
Toluene	116.4	155.2	97.7	77.0
Methyl isobutyl ketone	-	-	-	-
<u>Monomer composition</u>				
2-Hydroxyethyl methacrylate				
Acrylic acid	41.8	33.4	41.8	22.3
n-Butyl acrylate	18.5	21.6	15.4	12.3
n-Butyl methacrylate	64.3	105.6	78.7	22.8
2-Ethylhexyl methacrylate	55.4	79.4	-	50.6
Styrene	-	-	14.1	-
	-	-	-	12.0
<u>Polymerization initiator</u>				
Azobisisobutyronitrile	3.6	4.8	-	-
t-BPOEH *1	-	-	-	3.0
t-Butyl peroxybenzoate	-	-	2.3	-
Reaction temperature	reflux	reflux	reflux	reflux
Process 2				
<u>Monomers</u>				
α,α -Dimethylisopropenylbenzyl isocyanate	7.4	9.9	3.6	4.9
<u>Catalyst</u>				
Dibutyltin laurate	0.1	0.2	0.1	0.1
Reaction temperature	80°C	80°C	80°C	80°C

*1 t-BPOEH : t-Butylperoxy-2-ethylhexanoate

Table 5

Acrylic graft copolymer No.	(parts by weight)			
	A-2-1	A-2-2	A-2-3	A-2-4
Process 3				
<u>Solvent</u>				
Toluene	266.2	220.9	285.0	305.4
Methyl isobutyl ketone	-	-	-	-
<u>Monomer composition</u>				
2-Hydroxyethyl methacrylate	97.4	66.9	125.3	89.1
Acrylic acid	-	4.6	-	-
Methyl methacrylate	149.2	136.4	113.1	171.1
n-Butyl acrylate	173.4	152.1	211.6	171.8
Styrene	-	-	-	48.0
<u>Polymerization initiator</u>				
Azobisisobutyronitrile	6.3	-	-	-
t-BPOEH *1	-	-	-	9.6
t-Butyl peroxybenzoate	-	9.0	11.3	-
Reaction temperature	reflux	reflux	reflux	reflux

*1 t-BPOEH : t-Butylperoxy-2-ethylhexanoate

Table 6

Acrylic graft copolymer No.		A-2-1	A-2-2	A-2-3	A-2-4
Properties of the acrylic copolymer obtained in Process 1	Acid value				
	Hydroxyl value (mg KOH/g)	80	70	80	80
	Glass transition temp. (°C)	100	60	120	80
	Number av. mol. wt.	0	-10	-15	+20
Properties of the monomer combination polymerized in Process 3		4900	4900	8500	4900
	Acid value				
	Hydroxyl value (mg KOH/g)	0	10	0	0
	Glass transition temp. (°C)	100	80	120	80
Properties of the acrylic graft copolymer		+10	+10	0	+20
	Acid value				
	Hydroxyl value (mg KOH/g)	24	28	20	16
	Glass transition temp. (°C)	96	67	118	78
		+7	+2	-4	+20
	Number av. mol. wt.	32000	27000	45000	38000
	(al-2)/(mm-1) (w/w)	30/70	40/60	25/75	20/80
	(m-5)/(al-a) mol ratio	1.0	1.0	1.0	1.0

Preparation Example 4-1 [Making an aqueous dispersion]

After adding 80.0 parts of ethylene glycol monobutyl ether to 533.0 parts of acrylic graft copolymer A-2-1 obtained in Preparation Example 3-1, 5 207.3 parts of toluene were distilled off at decreased pressure. Dimethylmethanolamine 6.1 parts was added to this polymer solution (equivalent to 50% of the carboxyl groups), and after stirring 588.2 parts of deionized water was added and stirred to give a uniform 10 dispersion, and obtain a milky white low-viscosity aqueous dispersion A-2-1aq of acrylic graft copolymer A-2-1 (see Table 7).

15 Preparation Examples 4-2 to 4-4 [Making an aqueous dispersion]

Aqueous dispersions A-2-2aq to A-2-4aq of acrylic graft copolymers A-2-2 to A-2-4 were obtained by the same method as in Preparation Example 4-1 with the combinations in Table 7.

Table 7

Aqueous dispersion No.	A-2-1aq	A-2-2aq	A-2-3aq	A-2-4aq
Type of acrylic graft copolymer	A-2-1	A-2-2	A-2-3	A-2-4
Graft copolymer included	533.0	533.0	533.0	533.0
Ethylene glycol monobutyl ether	80.0	80.0	-	80.0
Methyl isopropyl ketone distilled off under decreased pressure	207.3	200.5	204.0	203.8
Toluene distilled off under decreased pressure	-	-	-	-
Dimethylethanamine	6.1	7.1	5.1	4.1
Deionized water	589.0	580.4	585.9	586.7
Nature of the aqueous dispersion obtained	milky white low-viscosity liquid	milky white low-viscosity liquid	milky white low-viscosity liquid	milky white low-viscosity liquid

Preparation Example 5-1 [Making internally non-crosslinked acrylic fine particle (B)]

Deionized water 606 parts and 3.0 parts of Ereminol ES-12 (surfactant; trade name Sanyo Chemicals) were put into a 4-mouthed flask fitted with a stirrer, a thermometer, a reflux cooling tube and a tube for introducing nitrogen gas, and held at 80°C stirred in a stream of nitrogen. Then 250.6 parts of a mixture (1) of 47.8 parts of n-butyl acrylate, 71.6 parts of methyl methacrylate, 30.6 parts of 2-hydroxyethyl acrylate, 0.6 parts of Ereminol ES-12 and 100 parts of deionized water was formed into a pre-emulsified dispersion and, stirring at 80°C, a polymerization initiator (1) of 0.6 parts of ammonium persulfate dissolved in 19.4 parts of deionized water was added dropwise in parallel with this emulsion over 2 hours. The mixture was stirred at 80°C for a further 1 hour to mature the core of the acrylic fine particles. Then 100.4 parts of pre-emulsified dispersion of a mixture (2) of 30 parts of n-butyl acrylate, 10.8 parts of 2-hydroxyethyl acrylate, 9.2 parts of methacrylic acid, 0.4 parts of Ereminol ES-12 and 50 parts of deionized water, and a polymerization initiator (2) of 0.2 parts of ammonium persulfate dissolved in 19.8 parts of deionized water were added dropwise in parallel over 1 hour. The reaction was completed by stirring at 80°C for a further 2 hours, to obtain internally non-crosslinked acrylic fine particles B-1 having an acid value of 30 mg KOH/g, a hydroxyl value of 100 mg KOH/g, a glass transition temperature of +3°C and a mean particle size of 60 nm. The mean particle size was determined in an aqueous medium using a NICOMP 370 Sub-micron Particle Sizer (trade mark Pacific Scientific Instrument Company) (see Table 8).

35

Preparation Example 5-2 to 5-4 [Making internally non-crosslinked acrylic fine particles (B)]

Internally non-crosslinked acrylic fine particles B-2 to B-4 were made by the same method as in

Preparation Example 5-1 with the combinations shown in Table 8.

Acrylic fine particle No.	B-1	B-2	B-3	B-4
<u>Put into the reaction tank</u>				
Deionized water	606	606	606	606
Ereminol ES-12 *1	3	3	3	3
<u>Mixture (1)</u>				
n-Butyl acrylate	47.8	46.7	46.4	67.5
Methyl methacrylate	71.6	71.6	71.6	82.5
2-Hydroxyethyl acrylate	30.6	31.7	32.0	-
Ereminol ES-12 *1	0.6	0.6	0.6	0.6
Deionized water	100	100	100	100
<u>Polymerization initiator (1)</u>				
Ammonium persulphate	0.6	0.6	0.6	0.6
Deionized water	19.4	19.4	19.4	19.4
<u>Mixture (2)</u>				
n-Butyl acrylate	30	25.0	10	28.4
2-Hydroxyethyl acrylate	10.8	9.7	9.4	12.4
Methacrylic acid	9.2	15.3	30.6	9.2
Ereminol ES-12 *1	0.4	0.4	0.4	0.4
Deionized water	50	50	50	50
<u>Polymerization initiator (2)</u>				
Ammonium sulfate	0.2	0.2	0.2	0.2
Deionized water	19.8	19.8	19.8	19.8
<u>Properties of the internally non-crosslinked acrylic fine particles (B)</u>				
Acid value (mg KOH/g)	30	50	100	30
Hydroxyl value (mg KOH/g)	100	100	100	30
Glass transition temperature (°C)	3	9	26	4
Mean particle size (nm)	60	80	100	60

*1 Trade name Sanyo Chemicals

Embodiments 1-11

5 Metallic water-based paint compositions having a solids content of 32 wt% were prepared on the basis of the combinations shown in Table 9 to Table 11 by adding
10 an aqueous dispersion obtained in Preparation Example 2-1 to 2-4 and Preparation Example 4-1 to 4-4, internally non-crosslinked acrylic fine particles B-1 to B-4 obtained in Preparation Example 5-1 to 5-4, aluminum paste (Alupaste 0539X; special processed
15 aluminum for water-based paint; heat residue 69 wt% (trade name Toyo Aluminum), an amino resin (Cymel 327; trade name Mitsui Scitec), an organic thickener swelled by alkalis (Primal ASE-60; trade name Rohm & Haas), dimethylethanolamine and deionized water. When the
20 solids content of the water-based paint composition was ≤ 32 wt% viscosity was adjusted without adding deionized water. These metallic water-based paint compositions were adjusted to a viscosity of 15 ± 2 ps using a B type viscosimeter at a rotation rate of 6 rpm, by adding water, and evaluated according to the afore-mentioned methods.

The results for appearance and performance of the resulting paint films, and the results for storage stability, are shown in Table 12.

[Table 9]

Embodiment No.	(parts by weight)			
	1	2	3	4
Aqueous dispersion				
A-1-1aq	517.2	-	-	-
A-1-2aq	-	517.2	-	-
A-1-3aq	-	-	517.2	-
A-1-4aq	-	-	-	517.2
A-2-1aq	-	-	-	-
A-2-2aq	-	-	-	-
A-2-3aq	-	-	-	-
A-2-4aq	-	-	-	-
Acrylic fine particles				
B-1	137.9	137.9	137.9	137.9
B-2	-	-	-	-
B-3	-	-	-	-
B-4	-	-	-	-
Dimethylethanolamine				
Cymel 327	3.3	3.5	3.6	3.7
Aluminum paste *1	91.9	91.9	91.9	91.9
Ethylene glycol monobutyl ether *2	59.9	59.9	59.9	59.9
Thickener *3	60.6	60.6	60.6	60.6
Deionized water	4.7	4.7	4.7	4.7
Deionized water to adjust viscosity	124.5	124.3	124.2	124.1
Total	15.9	32.2	66.7	103.4
Paint solids	1015.9	1032.2	1066.7	1103.4
	31.5%	31.0%	30.0%	29.0%

*1 Trade name Mitsui Scitec

*2 Alupaste 0539X (trade name Toyo Aluminum)

*3 Primal ASE-60 (trade name Rohm & Haas)

[Table 10]

(parts by weight)

Embodiment No.	5	6	7	8
Aqueous dispersion				
A-1-1aq	-	-	-	-
A-1-2aq	-	-	-	-
A-1-3aq	-	-	-	-
A-1-4aq	-	-	-	-
A-2-1aq	517.2	-	-	-
A-2-2aq	-	517.2	-	-
A-2-3aq	-	-	517.2	-
A-2-4aq	-	-	-	517.2
Acrylic fine particles				
B-1	137.9	137.9	137.9	137.9
B-2	-	-	-	-
B-3	-	-	-	-
B-4	-	-	-	-
Dimethylethanolamine	3.9	4.1	3.7	3.5
Cymel 327 *1	91.9	91.9	91.9	91.9
Aluminum paste *2	59.9	59.9	59.9	59.9
Ethylene glycol monobutyl ether	60.6	60.6	60.6	60.6
Thickener *3	4.7	4.7	4.7	4.7
Deionized water	123.9	123.7	124.1	124.3
Deionized water to adjust viscosity	122.8	142.9	103.4	49.2
Total	1122.8	1142.9	1103.4	1049.2
Paint solids	28.5%	28.0%	29.0%	30.5%

*1 Trade name Mitsui Scitac

*2 Alupaste 0539X (trade name Toyo Aluminum)

*3 Primal ASE-60 (trade name Rohm & Haas)

[Table 11]

(parts by weight)

Embodiment No.	9	10	11
Aqueous dispersion			
A-1-1aq	517.2	517.2	-
A-1-2aq	-	-	-
A-1-3aq	-	-	-
A-1-4aq	-	-	-
A-2-1aq	-	-	517.2
A-2-2aq	-	-	-
A-2-3aq	-	-	-
A-2-4aq	-	-	-
Acrylic fine particles			
B-1	-	-	-
B-2	137.9	-	-
B-3	-	137.9	-
B-4	-	-	137.9
Dimethylethanolamine	3.6	3.7	3.5
Cymel 327 *1	91.9	91.9	91.9
Aluminum paste *2	59.9	59.9	59.9
Ethylene glycol monobutyl ether	60.6	60.6	60.6
Thickener *3	4.7	4.7	4.7
Deionized water	124.2	124.1	124.3
Deionized water to adjust viscosity	66.7	142.9	122.8
Total	1066.7	1142.9	1122.8
Paint solids	30.0%	28.0%	28.5%

*1 Trade name Mitsui Scitec

*2 Alupaste 0539X (trade name Toyo Aluminum)

*3 Primal ASE-60 (trade name Rohm & Haas)

[Table 12]

Embodiment No.	1	2	3	4	5	6	7	8	9	10	11
<u>Dry film thickness</u>											
Undercoat (μm)	15	16	15	15	16	15	15	16	15	15	15
Clear coat (μm)	40	40	41	41	41	40	41	40	41	40	41
<u>Painted appearance</u>											
60° Gloss	93	93	95	94	93	95	94	94	95	93	95
Smoothness	o	o	o	o	o	o	o	o	o	o	o
Sagging	o	o	o	o	o	o	o	o	o	o	o
Al bittiness	o	o	o	o	o	o	o	o	o	o	o
<u>Paint film performance</u>											
Water-resistance	o	o	o	o	o	o	o	o	o	o	o
Resilience	o	o	o	o	o	o	o	o	o	o	o
Resistance to chemicals	o	o	o	o	o	o	o	o	o	o	o
<u>Storage stability</u>	o	o	o	o	o	o	o	o	o	o	o

Comparison Preparation Examples 1-45 1) Making an acrylic graft copolymer

Acrylic graft copolymers E-1 to E-4 were made by the same method as in Preparation Example 1 according to the formulations in Table 13 and Table 14. In E-1 the acid values of the hydrophilic acrylic copolymer (component (a1-1)) which becomes the stabilizing layer and of the final product are too high; in E-2 the hydroxyl value of the hydrophilic acrylic copolymer (component (a1-1)) which becomes the stabilizing layer is too low; in E-3 the acid values of the hydrophobic acrylic copolymer (monomer combination (a2-1)) which becomes the dispersion layer and of the final product are too high; and in E-4 the hydroxyl values of the hydrophobic acrylic copolymer (monomer combination (a2-1)) which becomes the dispersion layer and of the final product are too high.

[Table 13]

Acrylic graft copolymer No.	E-1	E-2
<u>Process 1 (parts by weight)</u>		
<u>Solvent composition</u>		
Methyl isopropyl ketone	95.5	-
Toluene	-	95.5
<u>Monomer composition</u>		
2-Hydroxyethyl methacrylate	34.8	3.5
Acrylic acid	28.9	19.4
n-Butyl acrylate	50.6	50.3
n-Butyl methacrylate	-	-
Methyl methacrylate	-	76.8
2-Ethylhexyl methacrylate	35.7	-
<u>Initiator</u>		
<i>t</i> -Butyl peroxybenzoate	4.5	4.5
Reaction temperature	reflux	reflux
<u>Process 2 (parts by weight)</u>		
<u>Solvent composition</u>		
Methyl isopropyl ketone	286.6	-
Toluene	-	286.6
<u>Monomer composition</u>		
2-Hydroxyethyl methacrylate	104.4	104.4
n-Butyl methacrylate	-	-
Acrylic acid	-	-
Methyl methacrylate	214.5	214.5
n-Butyl acrylate	131.1	131.1
Glycidyl methacrylate	4.4	4.4
<u>Initiator</u>		
<i>t</i> -BPOEH *1	9.0	9.0
Reaction temperature	reflux	reflux
<u>Properties of component (a1-1) obtained by Process 1</u>		
Acid value (mg KOH/g)	150	100
Hydroxyl value (mg KOH/g)	100	10
Glass transition temperature (°C)	0	+30
Number average molecular weight	4700	4800
<u>Properties of monomer combination (a2-1) polymerized in Process 2</u>		
Acid value (mg KOH/g)	0	0
Hydroxyl value (mg KOH/g)	100	100
Glass transition temperature (°C)	+30	+30
<u>Properties of the acrylic graft copolymer</u>		
Acid value (mg KOH/g)	34	22
Hydroxyl value (mg KOH/g)	100	78
Glass transition temperature (°C)	+22	+30
Number average molecular weight	31000	31000
Component (a1-1)/component (m-1) (w/w)	25/75	25/75
Component (m-3)/component (a1-1) mol ratio	1.0	1.0

*1 *t*-BPOEH : *t*-Butylperoxy-2-ethylhexanoate

[Table 14]

Acrylic graft copolymer No.	E-3	E-4
<u>Process 1 (parts by weight)</u>		
<u>Solvent composition</u>		
Methyl isopropyl ketone	95.5	95.5
Toluene	-	-
<u>Monomer composition</u>		
2-Hydroxyethyl methacrylate	34.8	34.8
Acrylic acid	19.4	19.4
n-Butyl acrylate	35.8	35.8
n-Butyl methacrylate	-	-
Methyl methacrylate	-	-
2-Ethylhexyl methacrylate	60.0	60.0
<u>Initiator</u>		
t-Butyl peroxybenzoate	4.5	4.5
Reaction temperature	reflux	reflux
<u>Process 2 (parts by weight)</u>		
<u>Solvent composition</u>		
Methyl isopropyl ketone	286.7	286.6
Toluene	-	-
<u>Monomer composition</u>		
2-Hydroxyethyl methacrylate	104.4	208.8
n-Butyl methacrylate	-	-
Acrylic acid	17.3	-
Methyl methacrylate	170.7	132.0
n-Butyl acrylate	157.5	109.2
Glycidyl methacrylate	4.4	4.4
<u>Initiator</u>		
t-BPOEH *1	9.0	9.0
Reaction temperature	reflux	reflux
<u>Properties of component (a1-1) obtained by Process 1</u>		
Acid value (mg KOH/g)	100	100
Hydroxyl value (mg KOH/g)	100	100
Glass transition temperature (°C)	0	0
Number average molecular weight	4700	4700
<u>Properties of monomer combination (a2-1) polymerized in Process 2</u>		
Acid value (mg KOH/g)	30	0
Hydroxyl value (mg KOH/g)	100	200
Glass transition temperature (°C)	+20	+30
<u>Properties of the acrylic graft copolymer</u>		
Acid value (mg KOH/g)	44	22
Hydroxyl value (mg KOH/g)	100	175
Glass transition temperature (°C)	+15	+22
Number average molecular weight	31000	31000
Component (a1-1)/component (m-1) (w/w)	25/75	25/75
Component (m-3)/component (a1-1) mol ratio	1.0	1.0

*1 t-BPOEH : t-Butylperoxy-2-ethylhexanoate

2) Making an aqueous suspension

Using the acrylic graft copolymers E-1 to E-4 obtained in 1) above, aqueous emulsions E-1aq to E-4aq of acrylic graft copolymers E-1 to E-4 were made by the
5 same method as in Preparation Example 2-1 with the combinations shown in Table 15.

Table 15

Aqueous dispersion No.	E-1aq	E-2aq	E-3aq	E-4aq
Type of acrylic graft copolymer	E-1	E-2	E-3	E-4
Graft copolymer included	533.0	533.0	533.0	533.0
Ethylene glycol monobutyl ether	80.0	80.0	-	80.0
Methyl isopropyl ketone distilled off under decreased pressure	203.0	-	203.0	-
Toluene distilled off under decreased pressure	-	203.0	-	203.0
Dimethylethanamine	8.6	5.6	11.1	5.6
Deionized water	581.4	584.4	578.9	584.4
Nature of the aqueous dispersion obtained	milky white low-viscosity liquid	milky white low-viscosity liquid	milky white low-viscosity liquid	milky white low-viscosity liquid

Note 1 : Low-viscosity means ≤ 1 ps at 25°C

Note 2 : Units parts by weight

Comparison Preparation Examples 5 and 6 [Making internally non-crosslinked acrylic fine particles]

Internally non-crosslinked acrylic fine particles were made by the same method as in Preparation Example 5, according to the formulations of Table 16. In the case of internally non-crosslinked acrylic fine particles F-1 the acid value was too low, and in F-2 the hydroxyl value was too high.

[Table 16]

Acrylic fine particle No.	F-1	F-2
<u>Put into the reaction tank</u>		
Deionized water	606	606
Ereminol ES-12 *1	3	3
<u>Mixture (1)</u>		
n-Butyl acrylate	47.8	16.8
Methyl methacrylate	71.6	40.0
2-Hydroxyethyl acrylate	30.6	93.2
Ereminol ES-12 *1	0.6	0.6
Deionized water	100	100
<u>Polymerization initiator (1)</u>		
Ammonium persulphate	0.6	0.6
Deionized water	19.4	19.4
<u>Mixture (2)</u>		
n-Butyl acrylate	37.7	10
2-Hydroxyethyl acrylate	10.8	30.8
Methacrylic acid	1.5	9.2
Ereminol ES-12 *1	0.4	0.4
Deionized water	50	50
<u>Polymerization initiator (2)</u>		
Ammonium sulfate	0.2	0.2
Deionized water	19.8	19.8
<u>Properties of the internally non-crosslinked acrylic fine particles (B)</u>		
Acid value (mg KOH/g)	5	30
Hydroxyl value (mg KOH/g)	100	300
Glass transition temperature (°C)	-4	2
Mean particle size (nm)	60	70

*1 Trade name Sanyo Chemicals

Comparison Examples 1-6

Water-based paint compositions were prepared as in the embodiments based on the combinations in Table 17 and Table 18. The water-based paint compositions obtained were evaluated by the same methods as for the embodiments. The results are shown in Table 19.

[Table 17]

Comparison Example No.	(parts by weight)		
	1	2	3
Aqueous dispersion			
E-1aq	517.2	-	-
E-2aq	-	517.2	-
E-3aq	-	-	517.2
E-4aq	-	-	-
A-1-1aq	-	-	-
Acrylic fine particles			
B-1	137.9	137.9	137.9
F-1	-	-	-
F-2	-	-	-
Dimethylethanolamine	4.9	3.5	5.2
Cymel 327 *1	91.9	91.9	91.9
Aluminum paste *2	59.9	59.9	59.9
Ethylene glycol monobutyl ether	60.6	60.6	60.6
Thickener *3	4.7	4.7	4.7
Deionized water	122.9	124.3	122.6
Deionized water to adjust viscosity	454.5	0.0	561.0
Total	1454.5	1000.0	1561.0
Paint solids	22.0%	32.0%	20.5%

10

*1 Trade name Mitsui Scitec

*2 Alupaste 0539X (trade name Toyo Aluminum)

*3 Primal ASE-60 (trade name Rohm & Haas)

[Table 18]

Comparison Example No.	(parts by weight)		
	4	5	6
<u>Aqueous dispersion</u>			
E-1aq	-	-	-
E-2aq	-	-	-
E-3aq	-	-	-
E-4aq	517.2	-	-
A-1-1aq	-	517.2	517.2
<u>Acrylic fine particles</u>			
B-1	137.9	-	-
F-1	-	137.9	-
F-2	-	-	137.9
Dimethylethanolamine	3.5	3.2	3.3
Cymel 327 *1	91.9	91.9	91.9
Aluminum paste *2	59.9	59.9	59.9
Ethylene glycol monobutyl ether	60.6	60.6	60.6
Thickener *3	4.7	4.7	4.7
Deionized water	124.3	124.6	124.5
Deionized water to adjust viscosity	142.9	0.0	66.7
Total	1142.9	1000.0	1066.7
Paint solids	28.0%	32.0%	30.0%

5

*1 Trade name Mitsui Scitec

*2 Alupaste 0539X (trade name Toyo Aluminum)

*3 Primal ASE-60 (trade name Rohm & Haas)

[Table 19]

Embodiment No.	1	2	3	4	5	6
<u>Dry film thickness</u>						
Undercoat (μm)	15	16	15	15	16	15
Clear coat (μm)	40	40	41	41	41	40
<u>Painted appearance</u>						
60° Gloss	90	91	90	92	89	93
Smoothness	o	o	o	o	o	o
Sagging	x	o	x	o	o	o
Al bittiness	o	o	o	o	x	o
<u>Paint film performance</u>						
Water-resistance	o	o	x	x	o	x
Resistance to chemicals	o	x	o	o	o	o
Storage stability	o	o	o	o	o	o

It is evident from the results of Table 19 that with Comparison Example 1 the proportion of painted solids of the resulting water-based paint composition is low so that sagging is produced and paint film appearance is inferior because the acid value of the acrylic graft copolymer E-1 is too high and the acid value of the stabilizing layer constituent of graft copolymer E-1 is too high.

With Comparison Example 2 the resistance of the resulting paint film to chemicals is inferior because the hydroxyl value of the stabilizing layer constituent of the acrylic graft copolymer E-2 is too low.

With Comparison Example 3 the proportion of painted solids of the resulting water-based paint composition is low so that sagging is produced and paint film appearance is inferior because the acid value of the acrylic graft copolymer E-3 is too high and the acid value of the dispersion layer constituent of graft copolymer E-3 is too high.

With Comparison Example 4 the water-resistance of the resulting paint film is inferior because the hydroxyl value of the acrylic graft copolymer E-4 is too high and the hydroxyl value of the dispersion layer constituent of the acrylic graft copolymer E-4 is too high.

With Comparison Example 5 the pseudoplastic properties of the resulting water-based paint composition are weak, so that aluminum bittiness is produced in the resulting paint film and appearance is inferior, because the acid value of the acrylic fine particles F-1 is low.

With Comparison Example 6 the resulting paint film is inferior in water-resistance because the hydroxyl value of the acrylic fine particles F-2 is high.

Claims

1. Water-based paint composition characterized in that it contains a water-dispersable acrylic graft copolymer
5 (A) which has an acid value of 10-30 mg KOH/g and a hydroxyl value of 50-150 mg KOH/g, which is a graft copolymer in which an acrylic copolymer (a1) which is a copolymer of α,β -ethylenic unsaturated monomers including an α,β -ethylenic unsaturated carboxylic acid
10 and has an acid value of 35-120 mg KOH/g and a hydroxyl value of 50-150 mg KOH/g, and an acrylic copolymer (a2) which is a copolymer of α,β -ethylenic unsaturated monomers and has an acid value of ≤ 15 mg KOH/g and a hydroxyl value of 50-150 mg KOH/g are graft polymerized
15 via chemical bonds, and internally non-crosslinked acrylic fine particles (B) which are of a copolymer made by emulsion polymerization of α,β -ethylenic unsaturated monomers (b1) and have an acid value of 15-200 mg KOH/g and a hydroxyl value of 15-200 mg
20 KOH/g,
with the proportions within the total resin solids in the water-based paint composition for which each accounts being 10-90 wt% for the water-dispersible acrylic graft copolymer (A), and 10-90 wt% for the
25 internally non-crosslinked acrylic fine particles (B).
2. Water-based paint composition according to Claim 1, characterized in that it contains an amino resin (C) of a number-average molecular weight of ≤ 1000 , accounting
30 for a proportion of 10-40 wt% of the total resin solids in the water-based paint composition.
3. Water-based paint composition according to Claim 1 or 2, characterized in that it contains an organic
35 thickener swelled by alkalis (D) at 0.1-5 wt% of the total resin solids in the water-based paint composition.
4. Water-based paint composition according to any of

the Claims 1-3, characterized in that the glass transition temperature of the acrylic copolymer (a1) is -20 to +50°C and its number average molecular weight is 4500-9000, the glass transition temperature of the

5 water-dispersible acrylic graft copolymer (A) is -20 to +50°C and its number average molecular weight is 10,000 to 100,000, and that the mean particle size of the internally non-crosslinked acrylic fine particles (B) in an aqueous medium is 20-150 nm.

INTERNATIONAL SEARCH REPORT

Internal Application No
PCT/EP 96/00107

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09D151/00 C09D133/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 292 004 (NIPPON PAINT CO LTD) 23 November 1988 see abstract; claims; examples see page 2, line 48 - page 4, line 50 ---	1-3
X	US,A,5 308 890 (SNYDER BARRY S) 3 May 1994 see abstract; claims; examples; tables see column 5, line 41 - line 57 ---	1,3,4
A	US,A,3 821 145 (WALUS A) 28 June 1974 see abstract; claims; examples see column 6, line 27 - line 31 ---	1-3
A	GB,A,2 060 654 (KANSAI PAINT CO LTD) 7 May 1981 see abstract; claims; examples -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *A* document member of the same patent family

Date of the actual completion of the international search

14 May 1996

Date of mailing of the international search report

07.06.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Mettler, R-M

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 96/00107

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0292004	23-11-88	JP-A- 63286473 US-A- 5011882	24-11-88 30-04-91
US-A-5308890	03-05-94	AU-B- 666245 AU-B- 5526994 BR-A- 9400672 CA-A- 2114711 CN-A- 1095084 CZ-A- 9400425 EP-A- 0612805 FI-A- 940897 JP-A- 7041683 NO-A- 940555 NZ-A- 250932 PL-A- 302395 US-A- 5344675 ZA-A- 9401117	01-02-96 01-09-94 01-11-94 27-08-94 16-11-94 19-10-94 31-08-94 27-08-94 10-02-95 29-08-94 21-12-95 05-09-94 06-09-94 26-08-94
US-A-3821145	28-06-74	NONE	
GB-A-2060654	07-05-81	JP-C- 1391663 JP-A- 56049759 JP-B- 61058101 JP-C- 1408540 JP-A- 56049760 JP-B- 62013991 CA-A- 1170388 DE-A- 3036408 US-A- 4329266	23-07-87 06-05-81 10-12-86 27-10-87 06-05-81 30-03-87 03-07-84 02-04-81 11-05-82